

Combined Weathering & Corrosion Testing

Applications, Methods, & Limitations

Charlie Lee (이응제 팀장)

IJ Inc

[녹음하기](#)

Housekeeping



We make testing simple.



You'll receive a follow-up email from info@email.q-lab.com with links to a survey, registration for future webinars, and to download the slides

- Our archived webinars are hosted at: q-lab.com/webinars
- Use the **Q&A feature in Zoom** to ask us questions today!



웹 세미나에 참석해 주셔서 감사합니다!

결합된 풍화 및 부식 테스트에 대한 웨비나가 도움이 되고 통찰력이 있기를 바랍니다. 아래 링크를 통해 슬라이드 및 녹화 된 웨비나에 액세스 할 수 있습니다.

웨비나 경험에 대한 3 개의 질문으로 구성된 설문 조사를 완료하여 가치 있고 고품질의 콘텐츠를 계속 제공하도록 도울 수 있습니다. 모든 피드백은 우리 팀원이 신중하게 검토합니다.



Topics

- Accelerated tests for product qualification
- History of combined weathering & corrosion testing
- Overview of current methods
- Recent Studies
- Reproducibility challenges

Matrix of Accelerated Tests

Accelerated Test Type	Result	Test Time	Results compared to	Research? Development? Certification?
Quality Control	Pass / fail	<ul style="list-style-type: none"> • Defined • Short 	Material specification	Certification & Research
Qualification / validation	Pass / fail	<ul style="list-style-type: none"> • Defined • Medium-long 	Reference material or specification	Certification & Development
Correlative	Rank-ordered data	<ul style="list-style-type: none"> • Open-ended • Medium 	Natural exposure (Benchmark site)	Development
Predictive	Service life Acceleration factor	<ul style="list-style-type: none"> • Open-ended • Long 	Natural exposure (Service environment)	Development & Warranty Contracts

What happens when your customer's qualification test gives incorrect data?

They still want their warranty!

Protective Coatings

Industrial Maintenance Coatings

Marine Coatings

- Primary job is to protect steel structures, industrial hardware, or other infrastructure in corrosive environments
- Sunlight exposure is often a factor
- Re-coating can be very expensive

Infrastructure Protection

- Bridges
- Metal buildings
- Petrochemical plants



Topics

- Accelerated tests for product qualification
- **History of combined weathering & corrosion testing**
- Overview of current methods
- Recent Studies
- Reproducibility challenges

Weathering and Corrosion



Weathering

Changes in material properties resulting from exposure to the radiant energy present in **sunlight** in combination with **heat** (including temperature cycling) and **water** in its various states, predominately as humidity, dew, and rain.



(Atmospheric) Corrosion

Deterioration and destruction of a material and its vital properties due to **electrochemical reactions** on the surface of a metal in an atmospheric environment. It occurs when the surface is **wet by moisture** formed due to rain, fog and condensation.

Combined Corrosion/Weathering

- Developed in the 1980s by Sherwin Williams



Combined Corrosion/Weathering

As a coating degrades from UV exposure, its ability to protect against corrosion is reduced



Combined Weathering/Corrosion Cycle



7 Days

UVA-340	4:00	0.89 W/m ² /nm	60°C
Condensation	4:00		50°C



7 Days, ASTM G85 A5


Fog (dilute solution)	1:00	24°C
Dry-off	1:00	35°C

Fluorescent UV Weathering Tester


QUV shown with new dual-touchscreen controller



UVA-340 Lamps




Condensation



Hot condensation is very effective at simulating moisture absorption in a wet environment such as Florida.

Continuous Salt Spray Salt Fog Environment




A solution of NaCl or other salts is pumped to an atomizing spray nozzle along with moisturized compressed air, creating a very fine mist that appears similar to fog.

Corrosion Specimen Evaluations

- *Corrosion creep along a scribe*
- Blistering
- Degree of rusting (ASTM D610)

Corrosion Along a Scribe

Coated Specimen (Metal Panel)




Scribing Tool




Scribe (cut) through the coating to the metal substrate


Expose the panel and allow corrosion to “creep” from the scribe



Corrosion Along a Scribe




Remove rust "scab"
with dull blade



Now the panel is ready
for evaluation

Corrosion Along a Scribe



Ignore corrosion areas near ends of scribe (approximately 6-12 mm)

Create grid lines (minimum of 6) from scribe perpendicular to edge of corroded areas—transparency can be placed over panel for this purpose

Measure distance between scribe and edge of corrosion

Paint removed due to loss of adhesion is a separate measurement


Corrosion Specimen Evaluations

Corrosion creep

Vs




Loss of adhesion
(cathodic
delamination)



In this study,
delamination data
from laboratory
tests correlated
best to outdoor
data


Salt Spray vs Outdoors

Salt Spray



Salt Spray for 2000 hours (1000 for latex)

Outdoor



27 months outdoor marine environment


Cyclic Wet/Dry vs Outdoors

**Prohesion
(ASTM G85 A5)**

Epoxy


Alkyd

Latex



Salt Spray for 2000 hours (1000 for latex)

Outdoor



27 months outdoor marine environment




Combined Corrosion/Weathering vs Outdoors

Epoxy

Alkyd




Latex

ASTM D5894



ASTM D5894 - for 2000 hrs

Outdoor



27 months outdoor marine environment

Corrosion/Weathering Validation

- **Society for Protective Coatings (SSPC)**
- Cleveland Society for Coatings Technology (CSCT)
- American Association of State Highway and Transportation Officials (AASHTO)

SSPC

- Society for Protective Coatings
- 15 different systems
- Outdoor vs. accelerated
 - 31 months
- Accelerated tests
 - Salt spray 5%
 - Prohesion
 - 2 types of cyclic immersion tests
 - Combined corrosion/ weathering test



SSPC Test Results

Laboratory Test Method	Correlation w/Severe Marine Environment
Conventional Salt Spray	-0.11
Prohesion	0.07
Cyclic Immersion Procedures	0.48
Cyclic Immersion with UV Procedure	0.61
Combined Corrosion/ Weathering Cycle	0.71

Results stated are Spearman rank coefficient 1.0 = perfect correlation, 0 = random, -1 = perfect rank reversal

Topics

- Accelerated tests for product qualification
- History of combined weathering & corrosion testing
- **Overview of current methods**
- Recent Studies
- Reproducibility challenges

ASTM D5894



7 Days

UVA-340	4:00	0.89 W/m ² /nm	60°C
Condensation	4:00		50°C



7 Days, ASTM G85 A5

Fog (dilute solution)	1:00	24°C
Dry-off	1:00	35°C

ASTM D5894 Variations

- NACE TM0304, TM0404
 - Replaces dilute $\text{NaCl}/(\text{NH}_4)_2\text{SO}_4$ solution with ASTM D1141 synthetic seawater
- Freeze cycling added to US Federal Highway Administration test

Synthetic Sea Water (ASTM D1141)

Compound	Concentration (g/L)
NaCl (sodium chloride)	24.53
MgCl ₂ (magnesium chloride)	5.20
Na ₂ SO ₄ (sodium sulfate)	4.09
CaCl ₂ (calcium chloride)	1.16
KCl (potassium chloride)	0.695
NaHCO ₃ (sodium bicarbonate)	0.201
KBr (potassium bromide)	0.101
All Others	<0.10

pH of synthetic seawater is 8.2









ISO 12944-6:2018

“Corrosion of steel structures by protective coating systems”

- Corrosivity categories described in ISO 12944-2 (based on ISO 9223)
- Durability classes described in ISO 12944-1
- ISO 12944-9 covers “off-shore” structures CX corrosivity classification (replaces ISO 20340)

ISO 12944-6

Annex B Cyclic Ageing Test

Day 1	Day 2	Day 3	Day 4	Day 5	Day 6	Day 7	
UV/condensation — ISO 16474-3			Neutral salt spray — ISO 9227			Low-temp. exposure at $(-20 \pm 2) ^\circ\text{C}$	
							

Repeat for 72 hours:
4 hours UVA-340, $0.83 \text{ W/m}^2/\text{nm}$ at 340 nm , 60°C
4 hours dark condensation, 50°C



72 hours of continuous salt fog at 35°C



Rinse panels and put in a freezer for 24 hours


Which Weathering/Corrosion Test is the Best?

- Actually, all generally exhibit good correlation to field studies
- Test severities are similar at equal duration

Topics


- Accelerated tests for product qualification
- History of combined weathering & corrosion testing
- Overview of current methods
- **Recent Studies**
- Reproducibility challenges

Correlation Study (Akzo Nobel)




Three systems perform similarly to continuous salt fog

Salt Fog versus Outdoor Coastal Exposure




Combined Weathering/Corrosion Cycles



ISO 20340/12944-9 vs NACE TM0304

	Acceptable				Excluded			
ISO 20340 6 months	Zn primer		Other		Zn primer		Other	
	≤3 mm		≤8 mm		>3 mm		>8 mm	
Scribe 2,0mm	S1	S2			S6		S9	
						S12		
					S4	S5	S3	
							S7	S8
							S10	S11
NACE rust creepage 3 months	Zn primer		Other		Zn primer		Other	
	<1,5 mm		<3,5 mm		>1,5 mm		>3,5 mm	
Scribe 2,0 mm	S1	S2			S6			
						S12		
					S4	S5	S3	
							S7	S8
							S10	S11
								S9



12 Coating systems on grit blasted steel panels
Pass/fail agreement on 11 of the 12 systems

ISO 20340/12944-9 and NACE methods have equal severity on a time scale

Nathalie LeBozec and Cecile Hall, French Corrosion Institute; Denis Melot, Total
NACE Corrosion 2014 Paper 3762

Reproducibility Concerns




Figure 2 : Corrosion extent from the scribe line after ISO 20340 Annex A test. Requirements for Zn Primer (<3mm) and non-Zn primer (<8mm) are highlighted.

- For 2 of 5 coating systems, all six labs agreed on pass/fail result
- 2 of 5 systems had multiple contradictory pass/fail results

Nathalie LeBozec, French Corrosion Institute; Laurence Bougon, CEREMA; John Carter, EXOVA; Tanja Scholz, Fraunhofer IFAM; Ole Oystien Knudsen, SINTEF; Adeline Flogard, SP Technical Research Institute of Sweden
NACE Corrosion 2016 Paper 6991

Topics

- Accelerated tests for product qualification
- History of combined weathering & corrosion testing
- Overview of current methods
- Recent Studies
- **Reproducibility challenges**

Reproducibility Case Study – Prohesion

- ASTM G85 Annex 5 (Prohesion)
- Part of ASTM D5894, modified in NACE standards

ASTM G85 Annex 5 (Prohesion)

1 Hour fog at “ambient” temperature (room should be 24°C)
1 hour dry-off 35°C

Solution: 0.05% NaCl
0.35% (NH₄)₂SO₄
pH: 5.0 - 5.4

ASTM G85 Annex 5 (Prohesion)

- How dry is dry?
- How long does it take to achieve a “dry” condition?

Answers are in the non-mandatory appendix:
“within $\frac{3}{4}$ hour all visible moisture is dried off the specimens”

Problem Statement

My new chamber isn't as severe as my old one


After 1000 hours of Prohesion, new chamber produced less severe results on a coatings test



Q-FOG CCT

Q-FOG CRH

Prohesion RH Profile in Two Chambers



Q-FOG CCT Cycle:

- Step 1: Fog 24°C 1:00
- Step 2: Dry 35°C 1:00
- Step 3: Go to Step 1

Q-FOG CRH Cycle:

- Step 1: Fog 24°C 1:00
- Step 2: RH 35°C, 25% RH 1:00
- Auto transition
- Step 3: Go to Step 1

Modified CRH Prohesion Cycle

Modified Prohesion Cycle:

Step 1: FOG 24°C 1:00


Step 2: RH 35°C, 95%RH 0:30

Auto transition

Step 3: RH 35°C, 25% RH 0:30

Auto transition

Step 4: Go to Step 1





Q-FOG CCT

Q-FOG CRH
(modified cycle)

Q-FOG CCT vs CRH


Q-FOG CCT has simple humidity generation without air flow and dry-off by blown heated air through chamber



Q-FOG CRH has atomizing humidification nozzles, an air drier (chiller), and a recirculation system with damper to regulate moist and dry air streams

Q-FOG CRH Linear and Auto Ramping

Transition from Wet to Dry



Improving Test Reproducibility

- Specify chamber RH and transition times of corrosion cycles
- Develop specimen handling instructions that reduce variability (lab conditions during handling, maximum time outside the chamber, whether rinsing should be performed)

Which technician runs the test?



or



**Thank you for your
attention!**

Questions?

info@q-lab.com
sales@ij-inc.com